



Date of test: 10 July 2013

Manufacturer's Declaration

Palziv's Vizion 2pcf FBZ has been tested in a *simulated* FAR 28.852a vertical 12s testⁱ in the Palziv laboratory, using a certified FTT UL94 chamber (<http://www.fire-testing.com/ul-94>) and achieved the following rating:

12.5mm (1/2") thick material:

Sample	Burn length	Flame time - sec.	Drip time
1	3.8"	6	0
2	4"	2	0
3	2.1"	2	0
4	2"	2.5	0
5	1.7"	2	0

The Palziv Internal Laboratory is not an accredited testing facility. The results are given in confidence, but for full confirmation, the test should be repeated at an accredited fire testing laboratory.



FAR requirements:

Test	Flame Time (sec)	Average Drip Extinguishing Time (sec.)	Average burn length
(i) 60 sec	< 15	< 3	152.40mm (6")
(ii) 12 sec	< 15	< 5	203.20mm (8")

A handwritten signature in blue ink, appearing to read "Gil Cimering".

Authorized by
Gil Cimering
CKO (Chief knowledge manager)
Palziv group

Palziv laboratory do not contain an official FAR 25.853 chamber for vertical fire tests. ⁱ