



Industry Compliance Vizion

Palziv North America 7966 NC 56Hwy Louisburg, NC 27549 919-497-0010

Standard for Approval	GMW15473 Type I
Product Description	V2.0 SEV

Properties	PNA Data	Standard Requirements	UOM	Status
Nominal Density (pcf)	2	Not Specified	Pcf	Pass
Tensile Strength	273	>50	kPa	Pass
Elongation	385	>100%	%	Pass
Tear Resistance		Not Specified		
Compression Deflection 50%	82	<5.0	kPa	Variance Required
Water absorption	<2%	<20%	%	Pass
MVSS302 FR Compliance	Gauge >.375"	<4" per Min	Inch/Min	Pass

Date of Compliance	8/9/12	QA Tech	JoAnn Burtness

Data represents typical values tested in accordance with written standards.

The information above on **Fuzion**[®] or **Vizion**[®] chemically cross-linked polyethylene foam is presented to the best of our knowledge. Results are measured by testing according to ASTM standards.

PNAQA-IC-001