



# Vizion



## Certificate of Analysis

Palziv North America  
 7966 NC 56Hwy Louisburg, NC 27549  
 919-497-0010  
[www.palzivna.com](http://www.palzivna.com)

Palziv Grade Designation: V8.0 STD 3" Grey 06  
 PXL's Part #: 0800T3F1NAGY40  
 PXL's Lot #: 35  
 Date Produced: 2/16/2012

<u>Physical Property</u>	<u>Test Method</u>	<u>UOM</u>	<u>Average Test Results</u>
Density	ASTM D3575 Suffix W	PCF	8.1
Tear Strength	ASTM D3575 Suffix G	lbf/in	43.8
Elongation	ASTM D3575 Suffix T	%	254
Tensile Strength	ASTM D3575 Suffix T	PSI	221.7
Compression Deflection 25% 50%	ASTM D3575 Suffix D	PSI	33.1
		PSI	55.1
Shore Hardness	ASTM D2240	OO	84

Lab Technician: Andrea Perrault

Date Completed: 3/8/2012

*PXL and its parent Palziv certify that this product was inspected and tested in accordance with written standards, and that the results are correct at the time of inspection. Due to the nature of the product, results will vary over time. The information above on Vizion® chemically cross-linked polyethylene foam is presented to the best of our knowledge. Tested at PXL Cobourg ON.*