



Fuzion 2.0 lb/ft<sup>3</sup> SEV

32 kg/m<sup>3</sup>

Effective Date: 2/17/2015

PHYSICAL PROPERTIES		TEST METHOD	IMPERIAL UNITS	VALUES	METRIC UNITS	VALUES
Density - Nominal		ASTM D3575 - Suffix W	lb/ft <sup>3</sup>	2.0	kg/m <sup>3</sup>	32
Tensile Strength	MD	ASTM D3575 - Suffix T	PSI	44.3	kPa	305
Tensile Strength	TD	ASTM D3575 - Suffix G		38.2		263
Tear strength	MD	ASTMD3575 - Suffix T	lbf/in	12.4	N/mm	2.17
Tear strength	TD	ASTM D3575 - Suffix G		13.0		2.27
Elongation at Break	MD	ASTM D3575 - Suffix T	%	205	%	205
Elongation at Break	TD	ASTM D3575 - Suffix T		212		212
Shore Hardness		ASTM D2440	00	48	00	48
Compression Deflection	25%	ASTM D3575 - Suffix D	PSI	5.1	kPa	35
	50%		PSI	13.5		93
Compression Set	25%, ½ hr	ASTM D3575 - Suffix B	%	16.5	%	16.5
	25%, 24 hrs			10		10
	50%, ½ hr			39		39
	50%, 24 hrs			30		30
Working Temperature Range			°F	-76 / 176	°C	-60 / 80
Water Absorption, 7 days		DIN 53428	% Vol (max)	1	% Vol (max)	1
Flammability, > 1/4"		FMVSS302	4"/min	PASS	100mm/min	PASS
Thermal Stability, 24 hrs at 158°F (70°C)		ASTM D3575 - Suffix S	%	2	%	2

Fuzion is a closed cell chemically crosslinked polyethylene foam in roll form.  
MSDS sheets available upon request.

Data represents typical values and should be considered as a guideline only.  
Imperial data is converted from the metric results measured by testing according to ASTM standards.  
The information above on Fuzion chemically crosslinked polyethylene foam is presented to the best of our knowledge.