



North American Headquarters
 7966 NC 56 Hwy Louisburg, NC 27549
 919.497.0010
www.palzivna.com

Certificate of Compliance

Standard for Approval	GMW15063- Type 5
PNA Product Description	F2.0 STD

Specification/Method	Results	Specified Value	Unit	Status
Fogging/VOCs- GMW3235 Method B-Y1-T1	0.9	≤ 4	mg	Meets
Flammability (as is)- GMW3232	75	< 100	mm/min	Meets (\geq 0.25" Thck.)
Flammability (aged)- GMW3232	93	< 100	mm/min	Meets (\geq 0.25" Thck.)
Interior Emissions- GMW15634	266	VOC ≤ 600	$\mu\text{g/g}$	Meets
Interior Emissions- GMW15634	202	SVOC ≤ 1000	$\mu\text{g/g}$	Meets
Resistance to Odor Wet Condition (Code A)- GMW3205	8.0	≥ 6	-	Deviation Req.
Resistance to Odor Dry Condition (Code B)- GMW3205	4.5	≥ 6	-	Meets
Mildew- GMW3259	N/A	No Mildew	-	N/A
Thickness- ISO 1923	6.1	Report	mm	Report
Dimensional Stability GMW4217	0.03	2 ± 0.5	%	Meets
Density- ISO 845	32 (nominal)	35 ± 5	kg/m^3	Meets
Compression Load Deflection 10% Deformation- ISO 844	16.3	>16	kPa	Meets
Compression Load Deflection 25% Deformation- ISO 844	35.7	Report	kPa	Report
Compression Load Deflection 50%- ISO 844	88.7	Report	kPa	Report
Tensile Strength- ISO 1926	278	Report	kPa	Report
Elongation at Break- ISO 1926	137	Report	%	Report
Comp Set 50%, 1/2hr- ISO 1856- B	45.5	Report	%	Report
Comp Set 50%, 24hr- ISO 1856- B	26.0	Report	%	Report

Date of Compliance:	4-Oct-16
---------------------	----------

Palziv North America certifies that this product was inspected and tested in accordance with written standards, and that the results are correct at the time of inspection. Due to the nature of the product, results will vary over time.

Authorized by

Joe Andolsen
 Testing Manager
 Palziv North America