



North American Headquarters  
 7966 NC 56 Hwy Louisburg, NC 27549  
 919.497.0010  
[www.palzivna.com](http://www.palzivna.com)

Certificate of Compliance				
Standard for Approval		WSS-M99P32-E1		
Product Description		Vizion V6.0 STD (1-step)		
Properties/Methods	Result	Specification Requirements	UOM	Status
3.3.2 Net Density (FLTM BN 106-01 Procedure B)	96 (nominal)	Report Units	kg/m <sup>3</sup>	-
3.4 Odor (FLTM BO 131-03, Variant A)	Cond. 1- 1, Cond. 2- 2, Cond. 3- 2, Cond. 4- 3	3 (max)	-	Pass
3.5 Fogging (SAE J1756, 16hr post test)	73	70 (min)	-	Pass
3.6 Flammability (FMVSS302)	40	100 (max)	mm/min	Pass
3.7.1 Resistance to Mildew (FLTM BO-131-03)	No Mildew /Odor	No Mildew/Odor	-	Pass
3.7.2.1 Short Term Environmental Cycling	No detrimental effect	No detrimental effect	-	Pass
3.7.2.2 Long Term Environmental Cycling	No detrimental effect	No detrimental effect	-	Pass
3.8.2 Tear Resistance (ASTM D3574 Test F) <sup>1</sup>	5915	Report Value	N/m	-
3.8.3 Compression Force Deflection (ASTM D3574 Test D)	215	Report Value	kPa	-
3.8.4.1 Constant Deflection Compression Set Original (ASTM D3574 Test D)	44.1	Report Value	%	-
3.8.4.2 Constant Deflection Compression Set After Short Term Env. Cycling (ASTM D3574 Test D)	3.4	40 (max)	%	Pass
3.8.4.2 Constant Deflection Compression Set After Long Term Env. Cycling (ASTM D3574 Test D)	7.9	10 (max)	%	Pass
3.8.6 Moisture Absorption (per method in spec.)	3.4	30 (max)	%	Pass
Date of Compliance:	12-Mar-18			

Palziv North America certifies that this product was inspected and tested in accordance with written standards, and that the results are correct at the time of inspection. Due to the nature of the product, results will vary over time.

1. Tested per ASTM D624 (per note in D3574 Test F)

Authorized by:

Joe Andolsen  
 Testing Manager  
 Palziv North America